



TC-5097

AHMEDABAD TEXTILE INDUSTRY'S RESEARCH ASSOCIATION

P.O. Ambawadi Vistar, Ahmedabad-380 015. India.
Ph. : (079) 26305131-7921-7922-7923 (Extn. No. : 346)
Sample Collection : 7990590718, Marketing : 9313541439
E-mail : ttl@atira.in Website : www.atira.in

**TEST REPORT**

Format No.: ATIRA/TT/24/001

ULR NUMBER TC 5097 26 2 00000764F		
Test Report No: A/T/2140	2025-26	Date: 02.03.2026
Mill/Company/Customer:	R for RABBIT BABY PRODUCTS PVT. LTD.	
Address & Contact Details:	R for Rabbit – 307, 3 rd Floor, Pinnacle Business Park, Corporate Road, Prahaladnagar, Ahmedabad, Gujarat –380015 Email :	
Sample forwarding Letter No. & Date:	Nil dated 18.02.2026	
Date of receipt of Sample:	21.02.2026	
Lab Sample Code No. :	TTCT – 4476	
Number of Samples : 01		
Date of Performance of test(s): 21.02.2026 to 02.03.2026		
Sample Description: Micro Modal Fabric (210 GSM)		

Discipline / Group : Mechanical Testing/ Textiles

Sr. No.	Test Parameters	Unit	Test Method	Test Results
1.	Count of Yarn removed from fabric	Ne	IS 3442	31.04
2.	Bursting strength	PSI	IS 1966	209.5
3.	Dimensional Change Wales Courses	%	ISO 6330 6N 60°C 1 Cycle	-2.84 -1.70
4.	Pilling Resistance	Rating	IS 10971	4-5

Discipline / Group : Chemical Testing / Textiles

Sr. No.	Test Parameters	Unit	Test Method	Test Results
1.	Colour fastness to washing Change In Colour Staining On Adjacent Polyester/Cotton/Viscose Nylon/Acrylic/Triacetate	Rating	ISO 105 C10 C(3), 60°C	4-5 4-5/4-5/4-5 4-5/4-5/4-5
2.	Colour fastness to perspiration Change In Colour Staining On Adjacent Polyester/Cotton/Viscose Nylon/Acrylic/Triacetate		ISO 105 E04	4-5 4-5/4-5/4-5 4-5/4-5/4-5
3.	Colour Fastness to Rubbing Dry Wet		ISO 105X12	4-5 4-5
4.	pH Value	--	IS 1390	6.96
5.	Blend Analysis Viscose Elastane	%	AATCC 20-20A	93.4 6.6

